REPORT DOCUMENTATION PAGE						Form Approved OMB NO. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comment regarding this burden estimates or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204. Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.							
AGENCY USE ONLY (Leave blair	nk)	2. REPORT DATE 7 July 97		3. REPORT TYPE A	AND DATES COVERED		
4. TITLE AND SUBTITLE Carbosilane & Carbosiloxane Based Graft Copolymers as Recyclable Multiphase Thermoplastic Materials 6. AUTHOR(S) K.B. Wagener and S.K. Cummings						HO4-94-6-0040	
7. PERFORMING ORGANIZATION NAMES(S) AND ADDRESS(ES) University of Florida Gainesville, F1 32611						FORMING ORGANIZATION ORT NUMBER	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) U.S. Army Research Office P.O. Box 12211 Research Triangle Park, NC 27709-2211					AGE	SUSPENSION OF THE SERVICE STATES OF THE SERV	
11. SUPPLEMENTARY NOTES			_				
The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by other documentation.							
12a. DISTRIBUTION / AVAILABILITY STATEMENT					12 b. DISTRIBUTION CODE		
Approved for public release; distribution unlimited.							
13. ABSTRACT (Maximum 200 words)							
The project goals are to investigate the use of unsaturated carbosilanes function alized with a Si-Cl bond in the synthesis of solvent resistant elastomers and high performance polymers. We have successfully synthesized a variety of chlorofunction alized carbosilane polymers which are highly elastic materials. Substitution on this highly elastic backbone with nucleophiles provided materials which were virtually insoluble in every solvent system studied. These solvent resistant materials have shown good thermal stability, being resistant to decomposition in air up to 400 degrees centigrade.							
DITC QUALITY INSPECTED 4							
14. SUBJECT TERMS						15. NUMBER IF PAGES	
chlorosilane, polymer, metathesis, copolymer, elastic						16. PRICE CODE	
17. SECURITY CLASSIFICATION		ECURITY CLASSIFICATION		SECURITY CLASSIFIC	ATION	20. LIMITATION OF ABSTRACT	
OR REPORT UNCLASSIFIED		THIS PAGE UNCLASSÍFIED		OF ABSTRACT UNCLASSIFIED	,	TIT.	

FINAL PROGRESS REPORT

TWO COPIES REQUIRED

1. ARO PROPOSAL NUMBER: 32545-CH

2. PERIOD COVERED BY REPORT: 1 January 1994 - 31 December 1996

3. TITLE OF PROPOSAL: Carbosilane & Carbosiloxane Based Graft Copolymers as Recyclable Multiphase Thermoplastic Materials

4. **CONTRACT OR GRANT NUMBER:** DAAH04-94-G-0040

5. NAME OF INSTITUTION: University of Florida

6. AUTHORS OF REPORT: K.B. Wagener and S.K. Cummings

7. LIST OF MANUSCRIPTS SUBMITTED OR PROPOSED UNDER ARO SPONSORSHIP DURING THIS REPORTING PERIOD, INCLUDING JOURNAL REFERENCES:

"Acyclic Diene Metathesis in the Preparation of Functionalized Carbosilane Polymers," S. Cummings, J. Anderson, and K. Wagener, *Polymer Preprints*, 37(2), 192 (1996).

"Access to Silicon-Derived Polymers via Acyclic Diene Metathesis Chemistry," S. Cummings, E. Ginsberg, R. Miller, J. Portmess, D. Smith, Jr., K. Wagener, in "Step Growth For High-Performance Materials: New Synthetic Methods," (ACS Symposium Series, No. 624), American Chemical Society, Washington, DC, 1996, Ch. 6.

"The Synthesis and Characterization of Chlorofunctionalized Unsaturated Carbosilane Oligomers and Polymers", J.D. Anderson, S.K. Cummings, J.D. Portmess, and K.B. Wagener, *Polymer Preprints*, 36(2), 162 (1995).

"Access to Silicon Derived Polymers Via ADMET Chemistry", S. Cummings, D. Smith, and K. Wagener, *Polymer Preprints*, **36**(1), 697, (1995).

"Synthesis and Characterization of a Chlorofunctionalized Unsaturated Carbosilane Oligomer", S.K. Cummings, D.W. Smith, and K.B. Wagener, *Macromol. Rapid Commun.*, **16**, 347 (1995).

19970820 048

8. SCIENTIFIC PERSONNEL SUPPORTED BY THIS PROJECT AND DEGREES AWARDED DURING THIS PERIOD:

S.K. Cummings, 5th Year Graduate Student J.D. Anderson, Postdoctoral Associate K. B. Wagener, Professor of Chemistry

9. **REPORTS OF INVENTIONS BY TITLE:**

None

APPROVED FOR PUBLIC RELEASE

DISTRIBUTION UNLIMITED

THE VIEWS, OPINIONS, AND/OR FINDINGS CONTAINED IN THIS REPORT ARE THOSE OF THE AUTHOR(S) AND SHOULD NOT BE CONSTRUED AS AN OFFICIAL DEPARTMENT OF THE ARMY POSITION, POLICY, OR DECISION, UNLESS SO DESIGNATED BY OTHER DOCUMENTATION.

K.B. Wagener Department of Chemistry University of Florida Gainesville, FL 32611

FINAL PROGRESS REPORT

Description of the research problem studied. Our work is related to the synthesis of a new class of silicon-based solvent resistant elastomers for military use. Such materials require demanding performance such as long-term durability, high solvent resistance, and usefulness over a wide temperature range. Typical applications include hoses, seals, mounting structures, face masks, and binding agents for advance projectile propellants. EMI shielding is also a potential area of use within military electronics.

Summary of the most important results. The project goals are to investigate the use of unsaturated carbosilanes functionalized with a Si-Cl bond in the synthesis of solvent resistant elastomers and high performance polymers. We have successfully synthesized a variety of chlorofunctionalized carbosilane monomers in high purity, which is required for the condensation metathesis polymerization technique used. Both monochloro carbosilane and dichloro carbosilane monomers were synthesized and were shown to be amenable to metathesis polymerization and afforded unsaturated carbosilane oligomers and polymers possessing the Si-Cl bond. The synthesis of this new elastic material consists of essentially two steps whereby the first consists of producing the chloro-functionalized carbosilane backbone, which in fact is highly elastic and reactive. We have successfully synthesized this backbone and characterized it completely with regard to structure, molecular weight, flexibility, and reactivity.

The second reaction consists of substituting on this highly elastic backbone with nucleophiles that will provide the solvent resistance that is sought. Both amine and alkoxide nucleophiles were employed in producing a material that is highly elastic, yet insoluble in virtually every solvent system studied. These solvent resistant materials have shown good thermal stability, being resistant to decomposition in air up to 400 degrees centigrade.

List of all publications and technical reports:

"Acyclic Diene Metathesis in the Preparation of Functionalized Carbosilane Polymers," S. Cummings, J. Anderson, and K. Wagener, *Polymer Preprints*, 37(2), 192 (1996).

"Access to Silicon-Derived Polymers via Acyclic Diene Metathesis Chemistry," S. Cummings, E. Ginsberg, R. Miller, J. Portmess, D. Smith, Jr., K. Wagener, in "Step Growth For High-Performance Materials: New Synthetic Methods," (ACS Symposium Series, No. 624), American Chemical Society, Washington, DC, 1996, Ch. 6.

"The Synthesis and Characterization of Chlorofunctionalized Unsaturated Carbosilane Oligomers and Polymers", J.D. Anderson, S.K. Cummings, J.D. Portmess, and K.B. Wagener, *Polymer Preprints*, 36(2), 162 (1995).

"Access to Silicon Derived Polymers Via ADMET Chemistry", S. Cummings, D. Smith, and K. Wagener, *Polymer Preprints*, **36**(1), 697, (1995).

"Synthesis and Characterization of a Chlorofunctionalized Unsaturated Carbosilane Oligomer", S.K. Cummings, D.W. Smith, and K.B. Wagener, *Macromol. Rapid Commun.*, **16**, 347 (1995).

Scientific personnel supported by this project and degrees awarded during this period.

S.K. Cummings, 5th Year Graduate Student J.D. Anderson, Postdoctoral Associate K. B. Wagener, Professor of Chemistry

Reports of invention by title. None.

Bibliography

- 1. J. M. Zeigler and F.W. Gordon Fearon, Eds., "Silicon-Based Polymer Science," American Chemical Society, Washington DC, 1990.
- 2. M. Zeldin, K.J. Wynne, H.R. Allcock, Eds., "Inorganic and Organometallic Polymers (Macromolecules Containing Silicon, Phosphorous and Other Inorganic Elements)"; American Chemical Society: Washington, DC, 1988, and references therein.
- 3. J.T. Goodwin, Jr., U.S. Patent 2, 607, 791, 1952. W.A. Kriner, J. Org. Chem., 29, 1601 (1964).
- 4. S. Yajima, Am. Ceram. Soc. Bull., 62, 893 (1983).
- 5. N.S. Nametkin, V.M. Vdovin, K.S. Pushchevaya, I. Zav'yalov, *Izv. Akad. Nauk SSSR*, Ser. Khim., 1453 (1965).
- 6. H.J. Wu, L.V. Interrrante, Macromolecules, 25, 1840 (1992).

- 7. N.S. Nametkin, V.M. Vdovin, Izv. Akad. Nauk SSSR, Ser. Khim., 1153 (1974).
- 8. W.P. Weber, X. Zhang, Q. Zhou, R.F. Horvath, T.H. Chan, and G. Manuel, *Macromolecules*, 21, 1563, (1988).
- 9. W.P. Weber, Y.T. Park, G. Manuel, *Macromolecules*, **23**, 1911 (1990). W.P. Weber, S.Q. Zhou, *Macromolecules*, **23**, 1915 (1990).
- 10. H. Lammens, G. Sartori, J. Siffert, and N. Srecher, J. Polym. Sci., Part B: Polym. Lett., 9, 341 (1971).
- 11. J.T. Anhaus, V.C. Gibson, W. Clegg, and S.P. Collingwood, *Organometallics*, 12, 1780, (1993).
- 12. D.W. Smith "Unsaturated Organosilicon Polymers Via Acyclic Diene Metathesis (ADMET) Condensation Polymerization, Ph.D. Dissertation, University of Florida 1992. K.B. Wagener, D.W. Smith, Jr., Macromolecules, 24, 6073 (1991). D.W. Smith, Jr., K.B. Wagener, Macromolecules, 26, 1633 (1993). D.W. Smith, Jr., K.B. Wagener, Macromolecules, 26, 3533 (1993).
- 13. S.K. Cummings, D.W. Smith, and K.B. Wagener, *Macromol. Rapid Commun.*, 16, 347, (1995). J.D. Anderson, S.K. Cummings, J.D. Portmess, and K.B. Wagener, *Polym. Prepr.*, (Am. Chem. Soc., Div. Polym. Chem.), 36, 162 (1995).
- 14. S. Cummings, E. Ginsberg, R. Miller, J. Portmess, D. Smith, Jr., K. Wagener in "Step-Growth Polymers For High-Performance Materials: New Synthetic Methods," J.L. Hedrick and J. W. Labadie, Eds., (ACS Symposium Series, No. 624), American Chemical Society, Washington, DC, 1996, Ch. 6.